

Branched Starch Molecules: Contribution to Ordered Structures
in
Granular Starch and Dispersed Starch Molecules

A highly branched homopolyglucan of MW up to 200×10^6 , the branched fraction of starch, amylopectin, occurs in nature in semi-crystalline form. This observation stands in sharp distinction to the behavior of other branched polymers. The highly ordered nature of the starch granule results from the non-random nature of the branching and the non-random distribution of the linear regions. Stable double helices of two linear regions of glucan chains are the basis for the regular packing in a crystalline array. Single helices from linear glucan regions can also form, around iodine (to form the familiar blue color) or around hydrophobic regions of organic molecules, especially monoacyl lipids.

The basis for starch granule and molecular order is the starch synthases and the branching enzymes. The resulting covalent and granule structure determines accessibility to amylolytic enzymes. The granule structure also determines how the granule will behave in industrial use (one important aspect of granule behavior is "gelatinization," which describes the loss of order prior to and during the swelling that occurs with sufficient heat and water, as the granule takes up water). Molecular structure determines granule structure and properties. In addition, molecular structure is responsible for the instability of starch molecules in the dispersed state (leading to subsequent molecular ordering, a phenomenon termed "retrogradation"). By judicious choice of processing conditions and starch source, one can take advantage of the kinetic constraints to reaching thermodynamic equilibrium, producing desirable metastable states of industrial interest.

In our laboratory we study a wide range of molecular architecture in maize starches, using starches obtained from maize endosperm genotypes with single and multiple lesions in the enzymes of the biosynthetic pathway. By comparing the nature of the molecular structure with physical behavior such as the endothermic phase transitions associated with loss of ordered structures, we can gain insight into physical properties of industrial importance, such as turbidity and gelation. Our research initially focused on the branched fractions alone. The *waxy* (*wx*) mutation leads to a starch that is solely amylopectin. In combination with other mutations, amylopectins of varied structure result. We have studied the structure of these amylopectin molecules. This work has continued in collaboration with Mark Guiltinan. We have explored the effects of various combinations of maize starch branching enzyme (SBE) isoforms on the amylopectin produced. We have developed novel enzymatic techniques to explore the nuances of the

branching pattern of these amylopectins, going well beyond a description of the standard chain length distribution to explore structures of the β -dextrins produced by β -amylase.

For the last several years we have worked with starches that have increased levels of the linear component, amylose. The *amylose-extender* (*ae*) mutant produces such starches, and their composition is modified by other mutations in combination. Even for these high-amylose starches, variation in the structure of the branched fraction can have a dominant influence on the behavior of the linear material. These starches are of special interest because they are resistant to digestion in the native state, and they can be manipulated physically and chemically to produce even higher levels of resistance to digestion. These sources of resistant starch (RS) are of great current interest as they appear to have a beneficial effect on colon health and by definition do not contribute to a glycemic response, as they are not digested in the small intestine. We have been awarded a patent for a granular starch high in RS, for which the level of RS is stable to subsequent thermal treatment. We are looking at novel ways to produce thermally stable RS from dispersed starches, a current line of work that has resulted in an invention disclosure.

References:

- Brockett, E., Thompson, D., Davis, T., and Boyer, C. 1988. Gelatinization characteristics of starch from *du*, *wx*, *ae*, and *ae wx* endosperm of sweet corn inbred Ia5125. *Starch/Starke* 40:175-177.
- Sanders, E.B., Thompson, D.B., & Boyer, C.D. 1990. Thermal behavior during gelatinization and amylopectin fine structure for selected maize genotypes as expressed in four inbred lines. *Cereal Chemistry* 67: 594-602.
- Yuan, C.-K.R., Thompson, D.B., and Boyer, C.D. 1993. Fine structure of amylopectin in relation to gelatinization and retrogradation behavior in maize starches from three *wx*-containing genotypes in two inbred lines. *Cereal Chemistry* 70: 81-89.
- Ziegler, G.R., Thompson, D.B., and Casasnovas, J. 1993. Dynamic measurement of starch granule swelling. *Cereal Chemistry* 70: 247-251.
- Shewmaker, C.K., Boyer, C.D., Wiesenborn, D.P., Thompson, D.B., Boersig, M.R., Oakes, J.V., and Stalker, D.M. 1994. Expression of *Escherichia coli* glycogen synthase in the tubers of transgenic potatoes (*Solanum tuberosum*) results in a highly branched starch. *Plant Physiology* 104: 1159-1166.
- Yuan, R.C. and Thompson, D.B. 1994. Sub-T_g thermal properties of amorphous waxy starch and its derivatives. *Carbohydrate Polymers*. 25: 1-6.
- Fisher, D.K., and Thompson, D.B. 1997. Retrogradation of maize starch after thermal treatment within and above the gelatinization temperature range. *Cereal Chemistry* 74: 344-351. [Retrogradation of waxy maize and *ae wx* maize starches was shown to vary according to the temperature to which the starch was cooked, and the effect was observed at temperatures far above those normally associated with complete gelatinization of waxy starch.]
- Yuan, R.C., and Thompson, D.B. 1998. Rheological and thermal properties of aged starch pastes from three waxy maize genotypes. *Cereal Chemistry* 75: 117-123. [In the formation of gels from three waxy-type starches, retrogradation was observed by rheological properties before it could be observed by DSC.]
- Yuan, R.C. and Thompson, D.B. 1998. Freeze-thaw stability of three waxy maize starch pastes measured by centrifugation and calorimetry. *Cereal Chemistry* 75: 571-573. [Extensively retrograded starches, as determined by DSC, were less susceptible to compression in centrifugation, and resulted in apparent recovery in freeze-thaw stability as determined by this method.]
- Liu, Q. and Thompson, D.B. 1998. Retrogradation of *du wx* and *su2 wx* maize starches following different gelatinization heat treatments. *Cereal Chemistry* 75: 868-874. [These two waxy-type maize starches were studied by the method of Fisher & Thompson (1997). In addition, retrogradation of the *du wx* starch was evaluated using the Avrami equation, and evidence was consistent with two mechanisms of retrogradation, depending upon the temperature of initial heating.]

- Klucinec, J. and Thompson, D.B. 1998. Fractionation of high-amylose maize starches by differential alcohol precipitation and chromatography of the fractions. *Cereal Chemistry* 75: 887-896. [High-amylose starches were fractionated by a two-step differential alcohol precipitation procedure, and the fractions were analyzed to determine the nature of the molecules present.]
- Boltz, K.W. and Thompson, D.B. 1999. Initial heating temperature and native lipid affects ordering of amylose during cooling of high-amylose starches. *Cereal Chemistry*. 76:204-212. [DSC exotherms observed on cooling of high-amylose starches varied according to the temperature of initial heating, suggesting that temperatures above 140°C are needed to enable the amylose of high-amylose starch granules to reassociate on cooling.]
- Liu, Q. and Thompson, D.B. 1999. Effects of moisture content and different gelatinization heating temperature on retrogradation of waxy-type maize starches. *Carbohydrate Research*. 314(3-4):221-235. [The waxy-type starches studied previously by Fisher & Thompson (1997) and by Liu & Thompson (1998) were examined as a function of starch solids as well as temperature of initial heating. The effect of altered moisture content differed for the four samples.]
- Klucinec, J. and Thompson, D.B. 1999. Amylose and amylopectin interact in the gelation of dispersed high-amylose starches. *Cereal Chemistry*. 76:282-291. [Gels prepared from molecularly dispersed starch fractions obtained from high-amylose starches (prepared as described by Klucinec & Thompson, 1998) were studied, and the mechanical and thermal properties during heating were compared to the same properties for gels prepared from the molecularly dispersed whole starch.]
- Thompson, D.B. 2000. On the non-random nature of amylopectin branching. *Carbohydrate Polymers*. 43:223-239. [A review of the current state of our understanding of the "fine structure" of amylopectin, with emphasis on the distribution of 1,6 branch points rather than the distribution of chain lengths. The concept of the ISL distribution is introduced.]
- Thompson, D.B. 2000. Strategies for the manufacture of resistant starch. *Trends Food Sci. Technol.* 11:245-253. [A review of information from the patent literature and elsewhere concerning the manufacture of enzyme-resistant starch.]
- Blauth, S. L., J. Klucinec, Y. Yuan, J.C. Shannon, D. B. Thompson, and M. J. Guiltinan. 2001. Identification of *Mutator* insertional mutants of starch branching enzyme 2a (*Sbe2a*) in *Zea mays* L. *Plant Physiol.* 125: 1396-1405. [The effect of inactivating maize SBEIIa on starch structure.]
- Brumovsky, J. and Thompson, D.B. 2001. Production of boiling-stable granular resistant starch by partial acid hydrolysis and hydrothermal treatments of high-amylose maize starch. *Cereal Chemistry* 78:680-689. [Although resistant starch levels decrease as a result of both annealing or heat-moisture treatment, the level of resistant starch that survives boiling is greater after both treatments. It is highest for heat-moisture treatment after partial acid hydrolysis.]
- Klucinec, J.D. and Thompson, D.B. 2002. Amylopectin structure and the amylose to amylopectin ratio both influence the nature of starch gels from mixtures of

amylopectin and amylose. *Cereal Chemistry* 79: 24-35. [Interaction of molecular dispersions of amylose and amylopectin is governed by the fine structure and MW of the amylopectin and also by the ratio of amylopectin to amylose.]

Klucinec, J.D. and Thompson, D.B. 2002. Structure of amylopectins from *ae*-containing maize starches. *Cereal Chemistry* 79: 19-23. [Amylopectins from several different high-amylose genotypes differ in fine structure, but all have enhanced levels of long B chains relative to short B chains.]

Blauth, S. L., J. Klucinec, J.C. Shannon, D. B. Thompson, and M. J. Gultinan. 2002. Identification of *Mutator* insertional mutants of starch branching enzyme I (*Sbe1*) in *Zea mays* L. *Plant Molec. Biol.* 48: 287-297. [The effect of inactivating maize SBEI on starch structure.]

Yao, Y., Gultinan, M.J., Shannon, J.C., & Thompson, D.B. 2002. Single kernel sampling method for maize starch analysis while maintaining kernel vitality. *Cereal Chemistry* 79:757-762. [Describes a means of testing endosperm starch structure such that seeds of interest may be grown to produce ears.]

Thompson, D.B. & Brumovsky, J. 2002. Manufacture of boiling-stable granular resistant starch by acid hydrolysis and hydrothermal treatment. U.S. patent no. 6,468,355. [Based on the publication by Brumovsky & Thompson, 2001.]

Evans, A. McNish, N, & Thompson, D. 2003. Polarization colors of lightly iodine-stained maize starches for amylose-extender and related genotypes in the W64A maize inbred line. *Starch/Starke* 55: 250-257. [Shows that amylose-extender (*ae*) maize starch granules appear pink, not blue when lightly stained and viewed through crossed polarizers. Granules from some high-amylose sources are quite heterogenous.]

Evans, A. and Thompson, D.B. 2004. Resistance to α -amylase digestion in four native high-amylose maize starches. *Cereal Chem.* 81: 31-37. [Describes differences in digestion pattern among granular high-amylose starches using α -amylase.]

Yao, Y., Thompson, D.B., & Gultinan, M.G. 2004. Maize starch-branching enzyme isoforms and amylopectin structure. In the absence of starch-branching enzyme IIb, the further absence of starch-branching enzyme Ia leads to increased branching. *Plant Physiol.* 136:3515-3523. [Presents the surprising finding that reduction in SBE activity actually leads to more branching. Also indicates that an effect of the mutation *sbe1a* is only evident in the presence of *ae*.]

Yao, Y., Gultinan, M.G., & Thompson, D.B. 2005. High performance size-exclusion chromatography (HPSEC) and fluorophore-assisted carbohydrate electrophoresis (FACE) to describe the chain length distribution of debranched starch. *Carbohydrate Research*. [Chain length information from FACE and HPSEC is directly related, and a more complete description of the chain length profile results than from either technique alone.]

Brumovsky, J.O., Brumovsky, L.A., & Thompson, D.B. 2006. A tentative explanation for the substantial rise of the gelatinization temperature of starch by adding salt and hydroxide. *Int.J.Food Properties* 9:889-896. [A description of how salts may stabilize starch granules during certain chemical modification treatments.]

- Li, J.-H., Guiltinan, M.J., & Thompson, D.B. 2006. The use of laser differential interference contrast microscopy for the characterization of starch granule ring structure. *Starch/Starke* 58:1-5. [A novel microscopic technique to visualize granule growth rings after partial acid hydrolysis.]
- Xia, H. & Thompson, D.B. 2006. Debranching of β -dextrins to explore branching patterns of amylopectins from three maize genotypes. *Cereal Chem.* 83:668-676. [An exploration of branching pattern of amylopectins from three genotypes, looking at differences in the structure of the β -dextrins produced during β -amylolysis.]
- Thompson, D.B. 2007. Resistant Starch, Chapter 2 (pp 73-95) in "Functional Food Carbohydrates," C.G. Biliaderis & M. Izydorczyk, eds. Taylor and Francis, Boca Raton, FL. [A review of the topic of resistant starch, emphasizing the idea that RS is a concept, not a chemical entity.]